

Bergadur™ PB40 G30 H UF natur UV

Polybutylene Terephthalate

PolyOne Corporation

Message:

Bergadur™ PB40 G30 H UF natur UV is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It is available in Europe.

Characteristics include:

- Flame Rated
- Flame Retardant
- Halogen Free
- UV Stabilized

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	UV Stabilizer		
Features	Flame Retardant		
	Halogen Free		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm³	ISO 1183
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9000	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	85.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	1.6	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	34	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	
Melting Temperature	224	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Glow Wire Flammability Index	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	4.0 to 6.0	hr	
Processing (Melt) Temp	230 to 270	°C	
Mold Temperature	65.0 to 95.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

