

# STARFLEX® P 7365

Thermoplastic Elastomer

STAR Thermoplastic Alloys & Rubbers, Inc.

Message:

STARFLEX® P 7365 Elastomer is an easy processing 65 Shore A hardness material designed for a wide variety of applications. STARFLEX® P 7365 Elastomer is supplied in pelletized form ready for thermoplastic processing.

STARFLEX® P 7365 Elastomer is a versatile product for use in injection molding, extrusion, blow molding and other thermoplastic fabricating techniques. Since STARFLEX® P 7365 Elastomer conducts heat well compared to polyolefins, molded parts cool quickly and relatively short cycle times are obtained. Scrap is 100 percent recyclable. The finished parts have sharp and well defined details.

General Information			
Features	Fast Molding Cycle		
	Good Processability		
	Good Weather Resistance		
	Recyclable Material		
Uses	Flexible Grips		
	Gaskets		
	Knobs		
Appearance	Black		
Forms	Pellets		
Processing Method	Blow Molding		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	1.4 to 1.7	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	65		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	2.41	MPa	ASTM D412
Tensile Strength (Break)	6.55	MPa	ASTM D412
Tensile Elongation (Break)	780	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	193 to 204	°C	
Front Temperature	204 to 216	°C	
Nozzle Temperature	216 to 232	°C	
Mold Temperature	26.7 to 65.6	°C	
Injection Pressure	3.45 to 4.83	MPa	

Injection Rate	Moderate-Fast	
Back Pressure	0.689 to 1.38	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

