# **Evermore PUR SS-143G**

## Polyurethane

Evermore Chemical Industry Co., Ltd.

#### Message:

Evermore PUR SS-143G is a Polyurethane product. It is available in Asia Pacific. Typical application: Fabrics/Fibers.

Nominal Value

29 to 31 DMF, MEK

Characteristics include:

Antiblock

High Gloss

**High Hardness** 

General Information			
Additive	Antiblock		
Features	Aliphatic		
	Antiblocking		
	High Gloss		
	High Hardness		
Uses	Synthetic Leather		
	Textile Applications		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	10.8 to 14.7	MPa	ASTM D412
Tensile Strength (Yield)	44.1 to 63.7	MPa	ASTM D412
Tensile Elongation (Break)	300 to 500	%	ASTM D412
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (25.0°C)	50.0 to 90.0	Pa·s	ASTM D3835

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Unit

%

Test Method

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Additional Information

Non-Volatile Content

Solvents

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

