

MAJORIS EB650 - 1199

Polypropylene

AD majoris

Message:

EB 650 - 1199 is a white, 60% mineral filled polypropylene compound intended for injection moulding.

The product is available in black (EB650-8229) and natural (EB650) but other colours can be supplied on request.

EB 650 WHITE 1199 has been developed especially for the automotive applications requiring very good sound insulation properties.

APPLICATIONS

Automotive components:

Parts requiring noise absorption

Electronic housings

Air ducts

Parts between engine and interior compartment

EB 650 - 1199 gives excellent properties for the parts requiring excellent rigidity, low shrinkage and high dimensional stability.

General Information			
Filler / Reinforcement	Mineral filler, 60% filler by weight		
Features	Good dimensional stability		
	Rigidity, high		
	Noise reduction		
	Recyclable materials		
	Low shrinkage		
Uses	Electrical housing		
	Sound insulation		
	Application in Automobile Field		
Appearance	White		
	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.85	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	19.0	MPa	ISO 527-2/50
Tensile Strain (Break)	3.0	%	ISO 527-2/50
Flexural Modulus ¹	3700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C)	4.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	25	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	112	°C	ISO 75-2/B
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	220 - 270	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

