

Ferro PP LPP35BF54HB-WH

Polypropylene

Ferro Corporation

Message:

Ferro PP LPP35BF54HB-WH is a Polypropylene material filled with 35% calcium carbonate. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

General Information			
Filler / Reinforcement	Calcium Carbonate,35% Filler by Weight		
Appearance	White		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	23	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	24.8	MPa	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Flexural Strength (Yield)	42.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Gardner Impact	6.78	J	ASTM D3029
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	202 to 204	°C	
Middle Temperature	204 to 210	°C	
Front Temperature	210 to 213	°C	
Nozzle Temperature	213 to 218	°C	
Mold Temperature	43.3 to 51.7	°C	
Back Pressure	0.345 to 0.689	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT