

# Clearflex® FG 336

Linear Low Density Polyethylene

Versalis S.p.A.

## Message:

Clearflex FG 336 is a hexene copolymer linear low density polyethylene (C6-LLDPE), additivated with antioxidant, slip agent, antiblocking agent and processing aid, suitable for blown film extrusion.

Films obtained from Clearflex FG 336 show high rigidity together with optimum Elmendorf tear and impact resistance.

Main Application

Clearflex FG 336 is recommended for shipping sacks, where the perfect balance between additivation (in terms of slip and antiblocking) and mechanical performances leads to the manufacture of a tough and easy peelable film. Moreover, for its sealing characteristics, together with low temperature mechanical resistance, Clearflex FG 336 is suggested for the production of freezer bags, either in coextrusion and in blend with LDPE.

General Information			
Additive	Antiblock		
	Antioxidant		
	Processing Aid		
	Slip		
Features	Antiblocking		
	Antioxidant		
	Copolymer		
	Food Contact Acceptable		
	Good Impact Resistance		
	Good Processability		
	Good Tear Strength		
	Good Toughness		
	Hexene Comonomer		
	High Rigidity		
	Low Density		
	Slip		
Uses	Bags		
	Blending		
	Film		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Blown Film		
	Coextrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.926	g/cm <sup>3</sup>	ISO 1183

Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.80	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (vs. Itself - Dynamic, Blown Film)	0.11		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Film Thickness - Recommended / Available	10 to 50μm		
Tensile Modulus			ISO 527-3
1% Secant, MD : 25 μm, Blown Film	180	MPa	
1% Secant, TD : 25 μm, Blown Film	200	MPa	
Tensile Stress			ISO 527-3
MD : Yield, 25 μm, Blown Film	12.0	MPa	
TD : Yield, 25 μm, Blown Film	13.0	MPa	
MD : Break, 25 μm, Blown Film	45.0	MPa	
TD : Break, 25 μm, Blown Film	36.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 25 μm, Blown Film	550	%	
TD : Break, 25 μm, Blown Film	740	%	
Dart Drop Impact <sup>1</sup> (25 μm, Blown Film)	120	g	ISO 7765-1
Elmendorf Tear Strength <sup>2</sup>			ISO 6383-2
MD : 25.0 μm	82.0	kN/m	
TD : 25.0 μm	250.0	kN/m	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	110	°C	ISO 306/A
Melting Temperature	127	°C	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 μm, Blown Film)	54		ASTM D2457
Haze (25.0 μm, Blown Film)	13	%	ISO 14782
Extrusion	Nominal Value	Unit	
Melt Temperature	190 to 230	°C	
NOTE			
1.	F50		
2.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

**Susheng Import & Export Trading Co.,Ltd.**

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

