

HiFill FR® PA6 3001 FR-NQ BK

Polyamide 6
Techmer Engineered Solutions

Message:

HiFill FR® PA6 3001 FR-NQ BK is a Polyamide 6 (Nylon 6) product. It can be processed by injection molding and is available in North America. Characteristics include:

Flame Rated
Flame Retardant
Heat Stabilizer
Lubricated

General Information			
Additive	Heat Stabilizer		
	Lubricant		
Features	Flame Retardant		
	Heat Stabilized		
	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.4	%	ASTM D955
Water Absorption (24 hr)	0.95	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	53.8	MPa	
Break	59.3	MPa	
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	2340	MPa	ASTM D790
Flexural Strength	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	68.3	°C	ASTM D648
CLTE - Flow	5.9E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	1.0E+12	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength ¹	21	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	232 to 257	°C	
Middle Temperature	232 to 257	°C	
Front Temperature	232 to 257	°C	
Processing (Melt) Temp	238 to 266	°C	
Mold Temperature	65.6 to 93.3	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
NOTE			

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT