

Pyramid™ PI010

Aromatic Polyimide
Polymics, Ltd.

Message:
Aromatic Polyimide, Unfilled

General Information			
Appearance	Yellow		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792
Water Absorption (23°C, 24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	57		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	86.0	MPa	ASTM D638
Tensile Elongation (Break)	7.0	%	ASTM D638
Flexural Modulus	3100	MPa	ASTM D790
Flexural Strength	110	MPa	ASTM D790
Coefficient of Friction (Dynamic)	0.29		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.318 mm)	4300	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	380	°C	ASTM D648
CLTE - Flow	5.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dissipation Factor (1 MHz)	2.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

