

# Durez® 156 (Injection)

Phenolic

Sumitomo Bakelite North America, Inc.

## Message:

Durez 156 Black Phenolic is a two-stage, heat resistant/electrical molding material. It exhibits excellent dimensional stability, high heat resistance, excellent molded appearance, and UL flammability rating. Typical applications include automotive carburetor spacers, sealing rings, thrust washers, speedometer sleeves, appliance terminals, probe controls, insulators, light baffles, etc.

General Information			
Features	Good dimensional stability Antibacterial property Heat resistance, high Good appearance		
Uses	Electrical/Electronic Applications Washer Isolated insulator Seals Application in Automobile Field		
Agency Ratings	MIL E-5272C		
Appearance	Black		
Forms	Particles		
Processing Method	Resin transfer molding Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm <sup>3</sup>	ASTM D792
Apparent Density	0.65	g/cm <sup>3</sup>	ASTM D1895
Molding Shrinkage - Flow	0.80	%	ASTM D6289
Water Absorption	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10300	MPa	ASTM D638
Tensile Strength	52.0	MPa	ASTM D638
Flexural Strength	83.0	MPa	ASTM D790
Compressive Strength	193	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	16	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	191	°C	ASTM D648

RTI Elec (3.00 mm)	160	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+12	ohms·cm	ASTM D257
Dielectric Strength			ASTM D149
-- <sup>1</sup>	14	kV/mm	ASTM D149
-- <sup>2</sup>	12	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.50		ASTM D2520
Dissipation Factor (1 MHz)	0.050		ASTM D150
Arc Resistance	180	sec	ASTM D495
Comparative Tracking Index	180	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.510 mm	V-1		UL 94
	V-0		
1.50 mm	5VA		UL 94
Thermoset	Nominal Value	Unit	
Shelf Life	52	wk	
Additional Information			
Test Specimens Molded at 340-350°F Typical transfer-molded shrinkage is 0.006 in/in Durez 156 is fungus resistant per Mil-E-5272C.			
NOTE			
1.	Method A (short time)		
2.	Method B (step by step)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

