

Sumiliteresin® PR-F-85G

Phenolic
SBHPP

Message:

PR-F-85G is a solid one-step resin, this is suitable for casting.
It can be called an environmentally-friendly resin that this product has the feature with low smell as it having a high reactivity.

General Information		
Features	High reactivity	
	Environmental protection	
Appearance	Brown	
Forms	flake	
Processing Method	Casting	
Physical	Nominal Value	Unit
Flow Length (125°C)	3.70	cm
Softening Point - B&R;	100	°C
Uncured Properties	Nominal Value	Unit
Gel Time (150°C)	0.75	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT