

Kepamid® 6130GFH

Polyphthalamide

Korea Engineering Plastics Co., Ltd

Message:

KEPAMID-PPA 6130GFH is a glass fiber 30%-reinforced PPA grade.

It is suitable for automotive, electrical & electronics, and consumer parts requiring excellent mechanical strength and heat resistance.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	High strength		
	Heat resistance, high		
Uses	Electrical/Electronic Applications		
	Application in Automobile Field		
	Consumer goods application field		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183
shrinkage-Flow (3.00 mm)	0.30 - 0.70	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	210	MPa	ISO 527-2
Tensile Strain (Break)	2.2	%	ISO 527-2
Flexural Modulus	10100	MPa	ISO 178
Flexural Stress	300	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	275	°C	ISO 75-2/A
Melting Temperature ¹	310	°C	ISO 11357-3
CLTE - Flow	2.2E-5 - 5.3E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Dielectric Strength	28	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	4.20		IEC 60250

Dissipation Factor (1 MHz)	2.0E-3		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			
Dry Air Dryer, A	90	°C	
Dry Air Dryer, B	120	°C	
Drying Time			
Dry Air Dryer, A	8.0	hr	
Dry Air Dryer, B	4.0	hr	
Suggested Max Moisture	0.10	%	
Hopper Temperature	60 - 80	°C	
Rear Temperature	310 - 330	°C	
Middle Temperature	310 - 335	°C	
Front Temperature	315 - 340	°C	
Nozzle Temperature	320 - 340	°C	
Mold Temperature	130 - 150	°C	
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT