

SynPlast™ TINTM-E

Triisononyl Trimellitate

PolyOne Corporation

Message:

Branched C9 trimellitate ester

General Information			
Uses	Cable sheath		
	Wire and cable applications		
	Insulating material		
Appearance	Clear/transparent		
Forms	Liquid		
Processing Method	Composite		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	0.971 - 0.981	g/cm ³	ASTM D4052
Acid Value ²	0.02	wt%	ASTM D1045
Molecular Weight ³	589		
Water content-Maximum	1000	ppm	ASTM D1533
Appearance	Clean, clean		ASTM D2090
Color ⁴	100		ASTM D1209
Viscosity-Kinematic			ASTM D445
25°C	330	cSt	ASTM D445
40°C	126	cSt	ASTM D445
100°C	11.9	cSt	ASTM D445
Ester content-Minimum value	99	%	ASTM D3465
Casting point	-40	°C	
Refractive index (25°C)	1.4840		
Additional Information			
包含 0.10-0.15 wt% 1,1,3-Tris (2-甲基-4-羟基-5-叔丁基 苯基)丁烷抗氧化剂			
NOTE			
1.	25/25°C		
2.	As TMA, the maximum		
3.	Theoretical value		
4.	Pt-Co grade, maximum		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

