

Teflon® PFA 440HPA

Perfluoroalkoxy
DuPont Fluoropolymers

Message:

For inventory control purposes product name may be followed by an X.
Products labeled PFA 440HPA and PFA 440HPA X are equivalent and all information in this document is applicable to both.

Typical Application

Applications for DuPont™ Teflon ® PFA 440HPA include fluid handling components for critical, high-purity processes like semiconductor, pharmaceutical, and biotechnology, as well as applications where purity in the parts-per-billion range is needed. Teflon ® PFA 440HPA offers a slightly higher melt flow rate than Teflon ® PFA 440HPB, providing greater processing ease.

Description

DuPont™ Teflon ® PFA 440HPA is a special purpose fluoroplastic resin available in pellet form. This resin is a chemically modified form of Teflon ® PFA 340 that combines many of the benefits of the parent resin (a relatively high typical melt flow rate of 16) with several additional benefits including enhanced purity, improved thermal stability while processing, and chemical inertness, for example, to ozonated fluids. Table 1 shows the typical property data for Teflon ® PFA 440HPA.

Teflon ® PFA 440HPA is a premium resin with the lowest level of extractables designed to meet ultra-high purity requirements. Teflon ® PFA 440HPA has a relatively high melt flow rate (typical MFR of 16) for injection molding and extrusion processes, and the highest level of inertness due to stable end group polymer structure. The enhanced purity of Teflon ® PFA 440HPA makes it suitable for applications that require improved color, lower extractable fluorides, and freedom from other foreign materials. This product contains no additives and is designed for hostile chemical environments where purity in the parts-per-billion range is needed. Examples are in semiconductor manufacture, fluid handling systems for industry or life sciences, and instrumentation for precise measurements of fluid systems. Compared to other thermoplastics, the high melt strength and thermal stability of Teflon ® PFA 440HPA can be used to improve processing rates, combining the processing ease of conventional thermoplastics with many properties similar to those of polytetrafluoroethylene.

Properly processed products made from neat Teflon ® PFA 440HPA resin provide the superior properties characteristic of fluoroplastic resins: chemical inertness, exceptional dielectric properties, heat resistance, toughness and flexibility, low coefficient of friction, non-stick characteristics, negligible moisture absorption, low flammability, performance at temperature extremes, and excellent weather resistance.

In a flame situation, products of Teflon ® PFA 440HPA resist ignition and do not promote flame spread. When ignited by flame from other sources, their contribution of heat is very small and added at a slow rate with very little smoke.

Teflon ® PFA 440HPA meets the requirements of ASTM D3307, Type I

General Information	
UL YellowCard	E54681-244682
Features	High purity
	Low friction coefficient
	Low hygroscopicity
	Low smoke
	Good electrical performance
	Good melt strength
	High liquidity
	Good chemical resistance
	Good weather resistance
	Heat resistance, medium
	Thermal stability, good
	Good toughness
	Compliance of Food Exposure
Uses	Liquid treatment
Agency Ratings	FDA 21 CFR 177.1550

Forms	Particle		
Processing Method	Extrusion		
	Resin transfer molding		
	Compression molding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	16	g/10 min	ASTM D3307, ISO 12086
Water Absorption (24 hr)	< 0.030	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D3307, ISO 12086
23°C	25.0	MPa	ASTM D3307, ISO 12086
250°C	14.0	MPa	ASTM D3307, ISO 12086
Tensile Elongation			ASTM D3307, ISO 12086
Fracture, 23°C	300	%	ASTM D3307, ISO 12086
Fracture, 250°C	480	%	ASTM D3307, ISO 12086
Flexural Modulus			ASTM D790, ISO 178
23°C	590	MPa	ASTM D790, ISO 178
250°C	55.0	MPa	ASTM D790, ISO 178
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	305	°C	ASTM D4591
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+18	ohms·cm	ASTM D257, ISO 1325
Dielectric Strength			
0.250 mm ¹	80	kV/mm	ASTM D149
0.250 mm	80	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	2.03		ASTM D150, IEC 60250
Dissipation Factor (1 MHz)	< 2.0E-4		ASTM D150, IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating ²	V-0		UL 94
Oxygen Index	> 95	%	ASTM D2863, ISO 4589-2
Additional Information	Nominal Value	Unit	Test Method
Critical Shear Rate (372°C)	56.0	sec ⁻¹	
MIT Folding Endurance ³ (200.0 μm)	1.5E+4	Cycles	ASTM D2176
Weather and Chemical Resistance: Outstanding			
NOTE			
1.	Method A (short time)		

2.

These results are based on laboratory tests under controlled conditions and do not reflect performance under actual fire conditions, current rating is a typical theoretical value.

3.

Depending on fabrication conditions

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

