

Scolefin 52 G 13-8

Polypropylene Homopolymer

Ravago Group

Message:

PPH GF20 grey

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Appearance	Grey		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Ash Content (625°C)	20	%	DIN EN 60
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4500	MPa	ISO 527-2
Tensile Stress (Yield)	65.0	MPa	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	35	kJ/m ²	ISO 179/1eU

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT