

ALTECH® PA6 C 2030/119 GF30IM

Polyamide 6
ALBIS PLASTIC GmbH

Message:

ALTECH® PA6 C 2030/119 GF30IM is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America. Characteristics include:
Flame Rated
REACH Compliant
RoHS Compliant
Impact Modified

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Impact Modifier		
Features		Impact Modified		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS Compliant		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.33	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	5.00	--	cm ³ /10min	ISO 1133
Water Absorption				ISO 62
Saturation, 23°C	7.0	--	%	
Equilibrium, 23°C, 50% RH	2.0	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	8400	--	MPa	ISO 527-2
Tensile Stress (Break)	135	--	MPa	ISO 527-2
Tensile Strain (Break)	3.2	--	%	ISO 527-2
Flexural Modulus	7400	--	MPa	ISO 178
Flexural Stress	200	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	14	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	70	--	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	206	--	°C	ISO 75-2/A
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	2.1E+11	ohms	IEC 60093
Volume Resistivity	1.8E+12	--	ohms · cm	IEC 60093

Comparative Tracking Index	400	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature - Desiccant Dryer	80.0		°C	
Drying Time - Desiccant Dryer	2.0 to 15		hr	
Suggested Max Moisture	0.15		%	
Processing (Melt) Temp	270 to 290		°C	
Mold Temperature	80.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

