

# SAMAT 666-3T

Polypropylene  
POLYROCKS CHEMICAL CO., LTD

Message:

SAMAT 666-3T is a Polypropylene product. It is available in Asia Pacific. Typical application: Electrical/Electronic Applications.  
Characteristics include:  
Flame Rated  
Chemical Resistant  
Flame Retardant  
Good Weather Resistance

General Information			
Features	Flame Retardant		
	Good Chemical Resistance		
	Good Weather Resistance		
Uses	Electrical/Electronic Applications		
UL File Number	E253482		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0 to 1.4	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.0	MPa	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	2800	MPa	ASTM D790
Flexural Strength	45.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	26	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	135	°C	ASTM D648
Ball Pressure Test (1.70 mm)	Pass		IEC 60695-10-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
3.00 mm	V-0		
Glow Wire Flammability Index	850	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	2.0	hr	

Processing (Melt) Temp	180 to 210	°C
Mold Temperature	40.0 to 70.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

