

Novalloy-A A5734

Acrylonitrile Butadiene Styrene + Nylon

Daicel Polymer Ltd.

Message:

Novalloy-A A5734 is an Acrylonitrile Butadiene Styrene + Nylon (ABS+Nylon) material. It is available in Asia Pacific. Primary attribute of Novalloy-A A5734: Flame Rated.

General Information				
UL YellowCard		E47773-239593		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.46	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.20 to 0.50	--	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.60	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	116	115		ISO 2039-2
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (Yield)	106	86.0	MPa	ISO 527-2
Flexural Modulus	6400	4800	MPa	ISO 178
Flexural Stress	171	136	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	12	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C, 6.40 mm)	110	--	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed, 6.40 mm	217	--	°C	ASTM D648
0.45 MPa, Unannealed	216	214	°C	ISO 75-2/B
1.8 MPa, Unannealed, 6.40 mm	198	--	°C	ASTM D648
1.8 MPa, Unannealed	194	190	°C	ISO 75-2/A
CLTE				ISO 11359-2
Flow	5.0E-5	--	cm/cm/°C	
Transverse	1.0E-4	--	cm/cm/°C	
Flammability	Dry	Conditioned		Test Method
Flame Rating (1.50 mm)	V-0	--		UL 94
Additional Information	Dry	Conditioned	Unit	
Moisture Content	--	1.0	%	
Injection	Dry	Unit		

Drying Temperature	90.0 to 100	°C
Drying Time	4.0 to 5.0	hr
Rear Temperature	180 to 210	°C
Middle Temperature	230 to 250	°C
Front Temperature	240 to 260	°C
Nozzle Temperature	230 to 250	°C
Mold Temperature	70.0 to 90.0	°C
Back Pressure	10.0 to 20.0	MPa
Screw Speed	50 to 80	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

