

# Sumiliteresin® PR-1306 BI

Phenolic

SBHPP

## Message:

SUMILITERESIN® PR-1306 BI is a straight novolak type powder with filler. It is generally apply for Fire Resistant Felt.

### Characteristics

SUMILITERESIN® PR-1306 BI is powder phenolic resin including hexamine, filler CaCO<sub>3</sub>, and flame retardant.

SUMILITERESIN® PR-1306 BI contained total filler 35±2%.

By using this type, The properties of flame test can be follow UL-94V-0

| General Information    |  |      |
|------------------------|--|------|
| Filler / Reinforcement | Calcium carbonate filler, 35% filler by weight |      |
| Additive               | Flame retardancy                               |      |
| Features               | Flame retardancy                               |      |
| Appearance             | White  |      |
|                        | Yellow   |      |
| Forms                  | Powder   |      |
| Physical               | Nominal Value                                  | Unit |
| Flow Length (125°C)    | 1.10   | cm   |
| Sieve Analysis - 106µm |  | %    |
| Hexa                   | 8.0  | %    |
| Uncured Properties     | Nominal Value                                  | Unit |
| Gel Time (150°C)       | 1.2  | min  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT