Wanthane® WHT-8190

Thermoplastic Polyurethane Elastomer (Polyether)

Wanhua Chemical Group Co., Ltd.

Message:

WHT-8180 is polyether-based TPU, supplied in form of transparent, translucent, colorless or slightly yellowish pellets with the characteristic of excellent hydrolytic stability, fungus resistance, low temperature flexibility & UV resistance.

Applications:

Wire & Cable, Film & Sheet, Hose & Tube, Animal Tag, Fire Hose, Sports Equipments etc.

General Information					
Features	Fungus Resistant				
	Good UV Resistance				
	Hydrolytically Stable				
	Low Temperature Flexibility				
Uses	Film				
	Hose				
	Sheet				
	Sporting Goods				
	Tubing				
	Wire & Cable Applications				
Appearance	Colorless				
	Translucent				
	Transparent - Slight Yellow				
Forms	Pellets				
Processing Method	Extrusion				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.12	g/cm³	ASTM D792		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	90		ASTM D2240		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Stress			ASTM D412		
100% Strain	10.0	MPa			
300% Strain	25.0	MPa			
Tensile Strength	28.0	MPa	ASTM D412		
Tensile Elongation (Break)	450	%	ASTM D412		
Tear Strength	100	kN/m	ASTM D624		

Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-40.0	°C	DSC
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	190	°C	
Middle Temperature	195	°C	
Front Temperature	200	°C	
Nozzle Temperature	205	°C	
Injection Pressure	75.0	MPa	
Extrusion	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0 to 4.0	hr	
Cylinder Zone 1 Temp.	190	°C	
Cylinder Zone 3 Temp.	195	°C	
Cylinder Zone 5 Temp.	200	°C	
Die Temperature	195	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

