

# Viton® GFLT-200S

Fluoroelastomer  
DuPont Performance Elastomers

Message:  
Low temperature peroxide curable FKM gums  
25 Mooney. Higher fluorine/low temperature type.

General Information			
Features	Solvent resistance		
	Compliance of Food Exposure		
Uses	Washer		
	Pipe		
	Pipe fittings		
	Metal bonding		
	Seals		
	Coating application		
Agency Ratings	FDA 21 CFR 177.2600 2		
Forms	Particle		
Processing Method	Extrusion		
	Resin transfer molding		
	Coating		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.86	g/cm <sup>3</sup>	ASTM D792
Mooney Viscosity	25	MU	ASTM D1646
Elastomers	Nominal Value	Unit	Test Method
Compression Set (200°C, 70 hr)	25	%	ASTM D395
Additional Information			

Nominal Viscosity, ML 1 + 10, 121°C: 25Polymer Fluorine Content: 67%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

