

CERTENE™ PHI-35

Polypropylene Homopolymer
Muehlstein

Message:

PHI-35 is a certified prime grade homopolymer Polypropylene designed for fiber spinning extrusion applications. PHI-35 combines a good balance of high flow processability with good tensile strength and chemical resistance. PHI-35 complies with FDA regulation 21CFR 177.1520 for all food contact up to a temperature of 100°C and most international regulations concerning the use of Polypropylene in contact with food.

General Information			
Features	Food Contact Acceptable		
	Good Chemical Resistance		
	Good Processability		
	High Flow		
	High Tensile Strength		
	Homopolymer		
Uses	Fibers		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Fiber (Spinning) Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.3	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT