NuSil R2-3930-11

Silicone

NuSil Technology

Message:

The Aircraft Industry has used silicone adhesives and coatings for over five decades. Silicone's ability to maintain its elasticity and low modulus over a broad temperature range provides excellent utility in extreme environments. Recent advances in material technology provide more opportunities for the Aircraft engineer in choosing the best material for an intended application. Examples of NuSil's capabilities in custom silicones for Aircraft are demonstrated in the following sections.

Fuel Resistance

Static Dissipation and Electrically Conductive Silicones

Ice-Phobic Coatings General Purpose: Coatings

Comment: 315 psi (2.2Mpa) Lap Shear at 7 D @ R.T., H/Fed. Color Standard 36622

General Information			
Features	Electrically Conductive		
	Fuel Resistant		
Uses	Aircraft Applications		
	Coating Applications		
Thermoset	Nominal Value	Unit	
Tack Free Time	20.0	min	
Cure System	Acetoxy		
Operating Temperature	-50 to 200	°C	
Uncured Properties	Nominal Value	Unit	
Color	Grey, Light		
Density	1.36	g/cm³	
Curing Time (23°C)	72	hr	
Cured Properties	Nominal Value	Unit	
Shore Hardness (Shore A)	40		
Lap Shear Strength ¹	2.17	MPa	
Tensile Strength	6.21	MPa	
Tensile Elongation at Break	400	%	
Tear Strength	10.5	kN/m	
NOTE			
1.	Primed with SP-130		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

