

EMERGE™ PC 4701-13

Advanced Resin

Trinseo

Message:

EMERGE™ PC 4701-13 Advanced Resin is formulated with 10% glass fiber and a proprietary flame retardant package. It provides superb ignition resistance, rigidity, dimension stability and heat resistance.

- Applications:
- Information technology equipment
 - Power tools
 - Electrical appliances and parts

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Flame Retardant		
	Good Dimensional Stability		
	High Heat Resistance		
	High Rigidity		
Uses	Appliances		
	Electrical/Electronic Applications		
	Power/Other Tools		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 3.20 mm, Injection Molded)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (3.20 mm, Injection Molded)	3650	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 3.20 mm, Injection Molded	65.5	MPa	
Break, 3.20 mm, Injection Molded	62.7	MPa	
Tensile Elongation (Break, 3.20 mm, Injection Molded)	4.0	%	ASTM D638
Flexural Modulus (3.20 mm, Injection Molded)	3790	MPa	ASTM D790
Flexural Strength (3.20 mm, Injection Molded)	109	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	110	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.20 mm, Injection Molded)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Annealed	149	°C	
1.8 MPa, Unannealed	141	°C	
1.8 MPa, Annealed	135	°C	
Vicat Softening Temperature	160	°C	ASTM D1525 ¹
Ball Indentation Temperature	> 125	°C	IEC 60335-1
CLTE - Flow (-40 to 80°C)	3.8E-5	cm/cm/°C	ASTM D696
RTI Elec	125	°C	UL 746
RTI Imp	110	°C	UL 746
RTI Str	125	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating ²			UL 94
1.59 mm	V-0		
3.20 mm	5VA		
Oxygen Index ³	38	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	288 to 316	°C	
Mold Temperature	82.2 to 116	°C	
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		
2.	This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.		
3.	This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

