ALFATER XL® A55I 4PA0001

Thermoplastic Vulcanizate

ALBIS PLASTIC GmbH

Message:

ALFATER XL®A55I 4PA0001 is a thermoplastic vulcanized rubber (TPV) product. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. ALFATER XL® The application areas of A55I 4PA0001 include electrical/electronic applications, engineering/industrial accessories, construction applications, sealing applications and the automotive industry.

Features include: Comply with REACH standard

ROHS certification Low emissions

General Information				
Features	Low volatilization			
	Good coloring			
	Ozone resistance			
	alkali resistance			
Uses	Handle			
	Plug			
	Electrical/Electronic Applications			
	Machine/mechanical parts			
	Building materials			
	Architectural application field			
	Connector			
	Seals			
	Application in Automobile Field			
Agency Ratings	EC 1907/2006 (REACH)			
RoHS Compliance	RoHS compliance			
Processing Method	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.920	g/cm³	ISO 1183	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	55		ISO 868	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress (100% Strain)	2.00	MPa	ISO 527-2	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress (Yield)	4.30	MPa	ISO 37	
Tensile Elongation (Break)	480	%	ISO 37	
Compression Set ¹ (100°C, 22 hr)	44	%	ISO 815	
Thermal	Nominal Value	Unit		

Service Temperature	-40 - 125	°C
Injection	Nominal Value	Unit
Drying Temperature - Circulation Dryer	70 - 80	°C
Drying Time - Circulation Dryer	2.0 - 4.0	hr
Processing (Melt) Temp	215 - 240	°C
Mold Temperature	70 - 90	°C
NOTE		
1.	25%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

