MAJORIS IB710

Polypropylene

AD majoris

Message:

IB710 is a white, mineral filled polypropylene compound intended for injection moulding.

The product is available in natural (IB710) and black (IB710 - 8229) but other colours can be supplied on request.

IB710 has been developed for applications where high density, good surface finish and good flow properties are necessary.

APPLICATIONS

High density products, such as:

Sound absorption parts

Electronic housings

Cosmetics mouldings

Appliances

| General Information | | | |
|--------------------------------------|-----------------------|----------|-----------------|
| Filler / Reinforcement | Mineral filler | | |
| Features | High density | | |
| | Recyclable materials | | |
| | Good liquidity | | |
| | Excellent appearance | | |
| | | | |
| Uses | Electrical housing | | |
| | Electrical appliances | | |
| | Sound insulation | | |
| | Cosmetics | | |
| | | | |
| Appearance | White | | |
| | Black | | |
| | Available colors | | |
| | Natural color | | |
| | | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 2.00 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2.1 | | | |
| kg) | 50 | g/10 min | ISO 1133 |
| Molding Shrinkage (2.00 mm) | 0.40 | % | Internal method |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Break) | 19.0 | MPa | ISO 527-2/5 |
| Tensile Strain (Break) | 2.0 | % | ISO 527-2/5 |
| Flexural Modulus ¹ | 4600 | МРа | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |

| Charpy Notched Impact Strength (23°C) | 2.1 | kJ/m² | ISO 179/1eA |
|--|---------------|-------|-------------|
| Charpy Unnotched Impact Strength (23°C) | 19 | kJ/m² | ISO 179/1eU |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature | | | |
| 0.45 MPa, not annealed | 120 | °C | ISO 75-2/B |
| 1.8 MPa, not annealed | 73.0 | °C | ISO 75-2/A |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | НВ | | UL 94 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 80.0 | °C | |
| Drying Time | 3.0 | hr | |
| Processing (Melt) Temp | 220 - 270 | °C | |
| Mold Temperature | 30.0 - 50.0 | °C | |
| Injection Rate | Moderate | | |
| Injection instructions | | | |
| Holding pressure: 50 to 70% of the injection | pressure | | |
| NOTE | | | |
| 1. | 2.0 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

