# HANWHA LLDPE 3224

### Linear Low Density Polyethylene

#### Hanwha Chemical

#### Message:

HANWHA LLDPE 3224 is manufactured by Unipol process and designed for general purpose and agricultural film . LLDPE 3224 has well balanced property of mechanical property and processability.

General Information					
Additive	Anti-caking agent				
	Antioxidation				
	slip agent				
Features	smoothness				
	Anti-caking property				
	Antioxidation				
	Workability, good				
	General				
Uses	Films				
	Agricultural application				
	3				
Agency Ratings	FDA 21 CFR 177.1520(c) 3.1a				
Forms	Particle	Particle			
Processing Method	Film extrusion				
	Blow film				
Physical	Nominal Value	Unit	Test Method		
Density	0.920	g/cm³	ASTM D1505		
Melt Mass-Flow Rate (MFR) (190°C/2.16					
kg)	2.0	g/10 min	ASTM D1238		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	18.1	МРа	ASTM D638		
Tensile Elongation (Break)	940	%	ASTM D638		
Films	Nominal Value	Unit	Test Method		
Film Thickness - Tested	30	μm			
Tensile Strength			ASTM D882		
MD: Break, 30 μm	37.3	МРа	ASTM D882		
TD: Break, 30 µm	35.3	MPa	ASTM D882		
Tensile Elongation			ASTM D882		
MD: Break, 30 μm	550	%	ASTM D882		
TD: Break, 30 µm	750	%	ASTM D882		

Dart Drop Impact (30 µm)	90	g	ASTM D1709
Tensile Tear Strength			ASTM D1004
MD : 30.0 μm	112.8	kN/m	ASTM D1004
TD : 30.0 μm	117.7	kN/m	ASTM D1004
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	101	°C	ASTM D1525
Peak Melting Temperature	122	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Haze (30.0 μm)	12	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	150 - 190	°C	
Extrusion instructions			
Extrusion instructions			

Blow-up Ratio: 2 to 3Optimum Gage Range: 0.03 to 0.1 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

