

# Gallonprene® GP520-7516

Thermoplastic Elastomer  
Shenzhen Sungallon Rubber & Plastic Corporation Limited

Message:

Gallonprene® GP520-7516 is a thermoplastic elastomer (TPE) product. It can be processed by injection molding and is available in Africa and the Middle East, Latin America or Asia Pacific. Gallonprene® GP520-7516 application areas include engineering/industrial accessories, electrical/electronic applications, household applications and sporting goods.  
Features include:  
Comply with REACH standard  
ROHS certification  
Halogen-free

General Information			
Features	High elasticity		
	Halogen-free		
Uses	overmolding		
	Plug		
	Household goods		
	Connector		
	Sporting goods		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	White		
	Rough surface polishing		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	30	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 23°C)	75		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Break)	11.0	MPa	ASTM D412
Tensile Elongation <sup>2</sup> (Break)	700	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	120 - 140	°C	
Middle Temperature	130 - 150	°C	
Front Temperature	140 - 160	°C	
Processing (Melt) Temp	110 - 130	°C	
Mold Temperature	30.0 - 60.0	°C	

Injection Rate	Moderate
Injection instructions	
Processing Temperature Limit: 260°CInjection Pressure: ModerateBack Pressure: 20 to 50%Overmolding Parameters:Rear Temperature: 150 to 170°CCenter Temperature: 160 to 180°CFront Temperature: 170 to 190°C Melt Temperature: 110 to 130°C Mold Temperature: 30 to 60°CProcessing Temperature Limit: 260°CInjection Pressure: ModerateInjection Speed: ModerateBack Pressure: 20 to 50%	
NOTE	
1.	500 mm/min
2.	500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

