

LEXAN™ BM5225X resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

BM5225X resin is a mineral filled grade featuring of high modulus, good flow and ductility, low warpage. It is of non-Br & non-Cl flame retardant systems intended to meet thin wall flame resistance and various environmental requirements.

General Information			
UL YellowCard	E207780-101019901		
Filler / Reinforcement	Mineral		
Features	Bromine Free		
	Chlorine Free		
	Ductile		
	Flame Retardant		
	Good Flow		
	Low Warpage		
Uses	Thin-walled Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.39	g/cm³	ASTM D792
--	1.40	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.20 to 0.30	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	109		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	5850	MPa	ASTM D638
--	5570	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	55.0	MPa	ASTM D638
Yield	56.0	MPa	ISO 527-2/5
Break ³	34.0	MPa	ASTM D638
Break	30.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	3.0	%	ASTM D638
Yield	3.0	%	ISO 527-2/5
Break ⁵	15	%	ASTM D638

Break	6.0	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	6020	MPa	ASTM D790
-- ⁷	6160	MPa	ISO 178
Flexural Stress			
--	98.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	98.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	7.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			ASTM D256
-30°C	50	J/m	
23°C	90	J/m	
Instrumented Dart Impact (23°C, Total Energy)	29.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	92.0	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹⁰	94.0	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	85.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹¹	87.0	°C	ISO 75-2/Af
Vicat Softening Temperature	98.0	°C	ASTM D1525 ¹²
CLTE			
Flow : 23 to 80°C	3.4E-5	cm/cm/°C	
Transverse : 23 to 80°C	7.2E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	V-1		
	V-0		
1.50 mm	5VB		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 105	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	16	hr	
Rear Temperature	250 to 270	°C	
Middle Temperature	260 to 280	°C	
Front Temperature	270 to 290	°C	
Nozzle Temperature	280 to 300	°C	
Processing (Melt) Temp	270 to 300	°C	
Mold Temperature	70.0 to 90.0	°C	
NOTE			

1.	5.0 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	Type I, 5.0 mm/min
5.	Type I, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4 mm
11.	80*10*4 mm
12.	Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

