LOXIM 510 01HB

Polycarbonate + ABS

LOXIM Industries Private Limited

Message:

LOXIM 510 01HB is a Polycarbonate + ABS (PC+ABS) product filled with 10% glass fiber. It is available in Asia Pacific. Primary characteristic: flame rated.

| General Information | | | | |
|---|---------------------------|----------------------------------|-------------|--|
| Filler / Reinforcement | Glass Fiber,10% Filler by | Glass Fiber,10% Filler by Weight | | |
| Appearance | Colors Available | | | |
| | Opaque | | | |
| | | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.20 to 1.25 | g/cm³ | ASTM D792 | |
| Molding Shrinkage - Flow | 0.40 to 0.60 | % | ASTM D1299 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength (Break) | 60.0 to 70.0 | MPa | ASTM D638 | |
| Flexural Modulus | 3000 to 3200 | MPa | ASTM D790 | |
| Flexural Strength | 90.0 to 100 | MPa | ASTM D790 | |
| Impact | Nominal Value | Unit | Test Method | |
| Notched Izod Impact (23°C) | 80 to 100 | J/m | ASTM D256 | |
| Unnotched Izod Impact (23°C) | 250 to 350 | J/m | ASTM D256 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Deflection Temperature Under Load (0.45 | | | | |
| MPa, Unannealed) | 115 to 125 | °C | ASTM D648B | |
| Flammability | Nominal Value | | Test Method | |
| Flame Rating (1.60 mm) | НВ | | UL 94 | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

