

TECHNO ABS 350

Acrylonitrile Butadiene Styrene

Techno Polymer Co, Ltd.

Message:

TECHNO ABS 350 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Asia Pacific or North America.

Characteristics include:

Flame Rated

High Flow

General Information			
UL YellowCard	E54297-244165		
Features	High Flow		
UL File Number	E54297		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	55	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.60	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	105		ASTM D785
R-Scale	104		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	41.2	MPa	ASTM D638
Yield	40.0	MPa	ISO 527-2
Flexural Modulus			
--	2350	MPa	ASTM D790
--	2130	MPa	ISO 178
Flexural Strength			
--	72.6	MPa	ASTM D790
--	63.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	23	kJ/m ²	ISO 179
Notched Izod Impact	230	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	88.0	°C	ASTM D648
0.45 MPa, Unannealed	77.0	°C	ISO 75-2/B
Flammability	Nominal Value		Test Method

Flame Rating (ALL)	HB	UL 94
Injection	Nominal Value	Unit
Drying Temperature	80.0 to 90.0	°C
Drying Time	2.0 to 5.0	hr
Rear Temperature	190 to 260	°C
Middle Temperature	190 to 260	°C
Front Temperature	190 to 260	°C
Mold Temperature	40.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

