

# Andur AL 80-5 AP-FP/Curene® 110

Polyurethane (Polyether, Aliphatic)

Anderson Development Company

## Message:

Andur AL80-5AP-FP is a polyether (PTMEG) based prepolymer terminated with an aliphatic isocyanate to improve color stability, hydrolytic stability, and give longer pot life.

General Information			
Features	Good color stability		
	Hydrolysis stability		
	aliphatic		
Forms	Liquid		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore A)	87		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	6.21	MPa	ASTM D412
300% strain	15.9	MPa	ASTM D412
Tensile Strength (Yield)	36.5	MPa	ASTM D412
Tensile Elongation (Break)	400	%	ASTM D412
Compression Set	45	%	ASTM D395B
Bayshore Resilience	41	%	ASTM D2632
Thermoset	Nominal Value	Unit	
Pot Life	5.0 - 7.0	min	
Demold Time (100°C)	30	min	
Post Cure Time			
21°C	72	hr	
100°C	16	hr	
Additional Information			
Durometer Hardness, ASTM D2240, Shore A: 85 to 88Die C Tear, ASTM D1004: 350 pliAverage Split Tear, ASTM D1938: 80 pliStoichiometry Curative Level: 95%Mix Temperature: Andur AL 80-5 AP-FP: 175°F Curene 110: 72°F			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

