

TAROLOX 111 G6 DX02

Polyethylene Terephthalate

Taro Plast S.p.A.

Message:

PET glass fiber reinforced 30%, self extinguishing V0 without PBDE/PBDF, high temperature resistance, good flow, very good mechanical, thermal and electrical properties, low moisture absorption, good dimensional stability. Product must be dried before moulding.
UL94 V0 approved all colours at 1,5 mm - V2 at 0,75 mm. UL 746B under testing.
Available: all colors, heat stabilized (H), release agent (W).

General Information			
UL YellowCard	E143048-467343		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
	Mold Release		
Features	Good Dimensional Stability		
	Good Electrical Properties		
	Good Flow		
	Good Mold Release		
	Heat Stabilized		
	High Heat Resistance		
	Low Moisture Absorption		
	Self Extinguishing		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.68	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.20 to 0.30	%	
Across Flow	0.60 to 0.80	%	
Water Absorption (23°C, 24 hr)	0.060	%	ASTM D570, ISO 62
Granule Humidity	< 0.030	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12000	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	2.0	%	ASTM D638, ISO 527-2
Flexural Modulus	11000	MPa	ASTM D790, ISO 178
Flexural Stress			
--	210	MPa	ISO 178
Break	210	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	70	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	240	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	244	°C	ISO 306/B50, ASTM D1525 1
Melting Temperature	256	°C	ASTM D211, ISO 121
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-2		
1.50 mm	V-0		
3.20 mm	V-0		
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
Oxygen Index	32	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	100 to 130	°C	
Injection Rate	Moderate-Fast		
NOTE			

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT