

RAMOFIN PPC343T4

Polypropylene Copolymer
Polyram Ram-On Industries

Message:
20% MINERAL FILLED, UV STABILIZED,HEAT STABILIZED POLYPROPYLENE FOR INJECTION MOULDING APPLICATIONS.

General Information			
Filler / Reinforcement	Mineral filler, 20% filler by weight		
Additive	heat stabilizer		
	UV stabilizer		
Features	Good UV resistance		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	1.4	%	ASTM D955
--	1.4	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ASTM D638, ISO 527-2
Tensile Strength (Yield)	20.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	75	%	ASTM D638, ISO 527-2
Flexural Modulus	1200	MPa	ASTM D790, ISO 178
Flexural Strength	30.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	80	J/m	ASTM D256
23°C	6.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	125	°C	ASTM D648, ISO 75-2/B
1.8 MPa, not annealed	69.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	155	°C	ASTM D1525, ISO 306
Melting Temperature	168	°C	ISO 11357-3, ASTM D3418
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	HB		UL 94
Flammability	22	mm/min	FMVSS 302

Injection	Nominal Value	Unit
Rear Temperature	190 - 220	°C
Middle Temperature	200 - 225	°C
Front Temperature	205 - 230	°C
Mold Temperature	30.0 - 65.0	°C
Injection Pressure	70.0 - 105	MPa
Holding Pressure	35.0 - 70.0	MPa
Back Pressure	0.350 - 0.700	MPa
Screw Speed	60 - 90	rpm
Injection instructions		

Fill Speed: 25 to 50 mm/sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

