

LUVOCOM® 1-9158

Polyamide 66
LEHVOSS Group

Message:

LUVOCOM® 1-9158 is a polyamide 66 (nylon 66) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of 1-9158 are:

Conductivity
anti-warping
Good stiffness

Typical application areas include:

textile/fiber
engineering/industrial accessories
Automotive Industry
business/office supplies

General Information			
Features	Conductivity		
	Heat conduction		
	Low warpage		
	Rigid, good		
	Static conduction		
	Good strength		
Uses	Textile applications		
	Engineering accessories		
	Application in Automobile Field		
	Business equipment		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/10.0 kg)	10	g/10 min	ISO 1133
Molding Shrinkage	0.60 - 1.3	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 1.3	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8000	MPa	ISO 527-2
Tensile Stress (Break)	40.0	MPa	ISO 527-2
Tensile Strain (Yield)	0.70	%	ISO 527-2
Flexural Modulus	7000	MPa	ISO 178
Flexural Stress	55.0	MPa	ISO 178
Flexural Strain at Flexural Strength	0.90	%	ISO 178

Maximum operating temperature-Short Term	140	°C	
Insulation Resistance	1.0E+2 - 1.0E+4	ohms	IEC 60167
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	100	°C	UL 746B
Thermal Conductivity ¹	28	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+4	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature			
Hot air dryer, A	75	°C	
Vacuum dryer, B	105	°C	
Drying Time			
Hot air dryer, A	6.0 - 16	hr	
Vacuum dryer, B	4.0 - 6.0	hr	
Rear Temperature	290 - 310	°C	
Middle Temperature	290 - 310	°C	
Front Temperature	290 - 310	°C	
Nozzle Temperature	280 - 300	°C	
Processing (Melt) Temp	290	°C	
Mold Temperature	90 - 120	°C	
Injection instructions			
<p>General</p> <p>In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.</p> <p>Lengthy dwell times for the melts in the cylinder should be avoided.</p> <p>Lower the temperatures during interruptions!</p> <p>Predrying (optional)</p> <p>It is advisable to predry the granulate with a suitable dryer immediately before processing.</p> <p>The granulate may absorb moisture from the air.</p> <p>Delivery Form & Storage</p> <p>Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.</p> <p>Preferably storage should be effected in dry and normally temperatured rooms</p> <p>Additional Information</p> <p>During processing the moisture level should not exceed 0.1%, otherwise molecular degradation and surface defects (e.g. smearing) may occur. Due to rapid absorption of water, originally sealed containers should only be opened immediately prior to processing. Excessively high predrying temperatures may cause discoloration.</p> <p>The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.</p> <p>Please contact us for further information.</p>			
NOTE			
1.	Hot-Disk, 60x60x3 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

