

# Cheng Yu FR200GV20

Polyamide 66

Cheng Yu Plastic Company Limited

Message:

Cheng Yu FR200GV20 is a Polyamide 66 (Nylon 66) product filled with 20% glass fiber. It is available in Asia Pacific.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.40 to 0.60	%	
Across Flow	1.1 to 1.3	%	
Water Absorption (Saturation)	1.0 to 2.0	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	110	MPa	ASTM D638
Flexural Strength	145	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	77	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	250	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	ASTM D257
Dielectric Constant (60 Hz)	3.50		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.500 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

