

AKROMID® B3 GF 40 1 L black (4581)

Polyamide 6 + PP
AKRO-PLASTIC GmbH

Message:

AKROMID® B3 GF 40 1 L black (4581) is a 40% glass fibre reinforced and heat stabilised polyamide-blend with a reduced density compared to standard PA6 GF 40
Applications are mainly technical components in the automotive and electronic industry, where a weight and cost reduction is required

General Information				
Filler / Reinforcement		Glass Fiber,40% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
		Low Density		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
Appearance		Black		
Resin ID (ISO 1043)		PA6 + PP GF40		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.36	--	g/cm ³	ISO 1183
Spiral Flow	65.0	--	cm	Internal Method
Molding Shrinkage				ISO 294-4
Across Flow	0.90	--	%	
Flow	0.40	--	%	
Humidity Absorption - 62% RH (70°C)	1.2	--	%	ISO 1110
Reinforcement Content	40	--	%	ISO 1172
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	11000	8400	MPa	ISO 527-2/1
Tensile Stress (Break)	160	115	MPa	ISO 527-2/5
Tensile Strain (Break)	3.2	4.2	%	ISO 527-2/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	15	15	kJ/m ²	
23°C	16	18	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	55	55	kJ/m ²	
23°C	70	66	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method

Heat Deflection Temperature				
0.45 MPa, Unannealed	217	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	201	--	°C	ISO 75-2/A
Melting Temperature ¹	220	--	°C	DIN EN 11357-1
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate ² (1.00 mm)	< 100	--	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB	--		UL 94
NOTE				
1.	10 K/min, DSC			
2.	> 1 mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

