

KUBE PIR 40253

High Density Polyethylene

KUBE Electronics AG

Message:

Transmissive Plastic Injection Molding Granulates

For fresnel lenses and windows of PIR motion detectors, thermal imaging cameras and non-contact thermometers

Features:

The best material for fresnel lenses

Specially suited for thin parts

High transmission in the 7 to 14 µm central passive infrared (PIR) band

Choice of colors and MFI

RoHS and TSCA conform

Excellent visible light absorption available for low false alarm rate / VDS conformity

Special colors available on request

According to KUBE's experience, these materials exhibit no substantial loss of specification over 10 years

40253: low density black / smoky

General Information			
Features	Flame Retardant		
	Good UV Resistance		
	Low Density		
Uses	Lenses		
	Thin-walled Parts		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Colors Available		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Density	0.951 to 0.960	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	17	g/10 min	ISO 1133
Injection	Nominal Value	Unit	
Drying Temperature	< 70.0	°C	
Drying Time	2.0	hr	
Hopper Temperature	50.0 to 70.0	°C	
Rear Temperature	170 to 220	°C	
Middle Temperature	200 to 220	°C	
Front Temperature	210 to 220	°C	
Nozzle Temperature	220 to 230	°C	
Processing (Melt) Temp	130	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

