

DOW™ LDPE 207M

Low Density Polyethylene Resin

The Dow Chemical Company

Message:

DOW™ LDPE 207M is a Low Density Polyethylene Resin material. It is available in Latin America. Primary attribute of DOW™ LDPE 207M: Slip.
Typical application of DOW™ LDPE 207M: Food Contact Applications

General Information			
Additive	Slip		
Agency Ratings	FDA 21 CFR 177.1520(c) 2.1		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.921	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.70	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.11		
vs. Itself - Static	0.15		
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Film Puncture Resistance (50 µm)	4.00	J/cm ³	Internal Method
Tensile Strength			ASTM D882
MD : Yield, 50 µm	10.0	MPa	
TD : Yield, 50 µm	10.0	MPa	
MD : Break, 50 µm	18.0	MPa	
TD : Break, 50 µm	16.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 50 µm	430	%	
TD : Break, 50 µm	660	%	
Dart Drop Impact (50 µm)	180	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 50 µm	290	g	
TD : 50 µm	230	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 50.0 µm)	41		ASTM D2457
Haze (50.0 µm)	13	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	206	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

