

MAJORIS EG304

Polypropylene

AD majoris

Message:

EG304 is a 30% chemically coupled glass fibre reinforced polypropylene compound intended for injection moulding. The product is available in natural, but other colours can be provided on request. EG304 has been developed especially for demanding applications in automotive industry and various engineering sectors. EG304 has high rigidity, good dimensional stability and good creep resistancy also at high temperatures. It has high flow rate and very good process ability.

APPLICATIONS

Product requiring high service temperature and extremely high mechanical strength such as:

Sockets and junction boxes for electrical industry

Electrical tool and appliance components

Miscellaneous technically items

Air filters

Car grilles

Lamp housing

Can suitably be made from EG304.

General Information	
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight
Additive	heat stabilizer
Features	Good dimensional stability
	Rigidity, high
	High strength
	Chemical coupling
	Recyclable materials
	Workability, good
	Good creep resistance
	High liquidity
	Heat resistance, high
Uses	Thermal Stability
	Electrical/Electronic Applications
	Power/other tools
	Filter
	Home appliance components
	Application in Automobile Field
Appearance	Shell
	Available colors
	Natural color
Forms	Particle

Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ISO 1133
Molding Shrinkage	0.40 - 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	83.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	2.5	%	ISO 527-2/50
Flexural Modulus ¹	5600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	37	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	159	°C	ISO 75-2/B
1.8 MPa, not annealed	145	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	230 - 270	°C	
Mold Temperature	30.0 - 70.0	°C	
Injection Rate	Slow-Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

