ELASTOSIL® LR 3003/70 A/B

Silicone

Wacker Chemie AG

Tensile Elongation at Break

Compression Set

Rebound Resilience

Electric Strength

Volume Resistivity

Dissipation Factor (50 Hz)

Tear Strength

Message:

Silicone Rubber, LSR
Molded Seals, Plastics and Rubber Processing
Molded Parts, Automotive, Plastics and Rubber Processing
Molded Parts, Food Contact, Plastics and Rubber Processing
Molded Parts, Technical, Plastics and Rubber Processing
Vibration Dampers, Automotive & Transportation
Spark Plugs Boots, Automotive & Transportation

General Information			
Features	Food Contact Acceptable		
	General Purpose		
Uses	Automotive Applications		
	Automotive Under the Hood		
	Gaskets		
	Membranes		
	Seals		
	Valves/Valve Parts		
Processing Method	Injection Molding		
	Liquid Injection Molding (LIM)		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.14	g/cm³	ISO 1183
Viscosity	450	Pa∙s	DIN 53019
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	70		DIN 53505
Tensile Strength	8.60	MPa	DIN 53504

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

290

13

21.0

71

23

5.0E+15

2.0E-3

%

kN/m

kV/mm

ohms·cm

DIN 53504

DIN ISO 815-B

ASTM D624B

DIN 53512

DIN IEC 243

DIN IEC 93

DIN VDE 0303

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2