

# NOVADURAN® 5010GN1-30AM2

Polybutylene Terephthalate

Mitsubishi Engineering-Plastics Corp

## Message:

NOVADURAN® 5010GN1-30AM2 is a Polybutylene Terephthalate (PBT) material filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of NOVADURAN® 5010GN1-30AM2 are:

Flame Rated

Flame Retardant

| General Information                     |                                  |                   |             |
|-----------------------------------------|----------------------------------|-------------------|-------------|
| Filler / Reinforcement                  | Glass Fiber,30% Filler by Weight |                   |             |
| Additive                                | Flame Retardant                  |                   |             |
| Features                                | Flame Retardant                  |                   |             |
| Forms                                   | Pellets                          |                   |             |
| Processing Method                       | Injection Molding                |                   |             |
| Physical                                | Nominal Value                    | Unit              | Test Method |
| Density                                 | 1.66                             | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage                       |                                  |                   |             |
| Across Flow : 2.00 mm                   | 1.2                              | %                 |             |
| Flow : 2.00 mm                          | 0.50                             | %                 |             |
| Water Absorption (Saturation, 23°C)     | 0.070                            | %                 |             |
| Mechanical                              | Nominal Value                    | Unit              | Test Method |
| Tensile Modulus                         | 11000                            | MPa               | ISO 527-2   |
| Tensile Stress (Break)                  | 140                              | MPa               | ISO 527-2   |
| Tensile Strain (Break)                  | 2.0                              | %                 | ISO 527-2   |
| Flexural Modulus                        | 10500                            | MPa               | ISO 178     |
| Flexural Stress                         | 220                              | MPa               | ISO 178     |
| Impact                                  | Nominal Value                    | Unit              | Test Method |
| Charpy Notched Impact Strength (23°C)   | 10                               | kJ/m <sup>2</sup> | ISO 179     |
| Charpy Unnotched Impact Strength (23°C) | 46                               | kJ/m <sup>2</sup> | ISO 179     |
| Thermal                                 | Nominal Value                    | Unit              | Test Method |
| Heat Deflection Temperature             |                                  |                   |             |
| 0.45 MPa, Unannealed                    | > 220                            | °C                | ISO 75-2/B  |
| 1.8 MPa, Unannealed                     | 206                              | °C                | ISO 75-2/A  |
| Melting Temperature                     | 224                              | °C                | ISO 11357-3 |
| CLTE                                    |                                  |                   | ISO 11359-2 |
| Flow : -30 to 50°C                      | 2.0E-5                           | cm/cm/°C          |             |
| Flow : -30 to 120°C                     | 1.0E-5                           | cm/cm/°C          |             |
| Flow : 50 to 120°C                      | 1.0E-5                           | cm/cm/°C          |             |
| Transverse : -30 to 50°C                | 8.0E-5                           | cm/cm/°C          |             |

| Transverse : -30 to 120°C        | 1.0E-4        | cm/cm/°C |             |
|----------------------------------|---------------|----------|-------------|
| Transverse : 50 to 120°C         | 1.4E-4        | cm/cm/°C |             |
| Electrical                       | Nominal Value | Unit     | Test Method |
| Surface Resistivity              | 6.0E+15       | ohms     | IEC 60093   |
| Volume Resistivity               | 3.0E+16       | ohms·cm  | IEC 60093   |
| Electric Strength (1.00 mm)      | 24            | kV/mm    | IEC 60243-1 |
| Relative Permittivity (1 MHz)    | 3.90          |          | IEC 60250   |
| Dissipation Factor (1 MHz)       | 0.014         |          | IEC 60250   |
| Comparative Tracking Index (CTI) | PLC 3         |          | UL 746      |
| Flammability                     | Nominal Value | Unit     | Test Method |
| Flame Rating (0.710 mm)          | V-0           |          | UL 94       |
| Injection                        | Nominal Value | Unit     |             |
| Drying Temperature               | 120           | °C       |             |
| Drying Time                      | 5.0 to 8.0    | hr       |             |
| Rear Temperature                 | 235           | °C       |             |
| Middle Temperature               | 240           | °C       |             |
| Front Temperature                | 255           | °C       |             |
| Nozzle Temperature               | 250           | °C       |             |
| Mold Temperature                 | 80.0 to 100   | °C       |             |
| Injection Pressure               | 20.0 to 150   | MPa      |             |
| Screw Speed                      | 80 to 120     | rpm      |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

