

Lustran® SAN DN52

Styrene Acrylonitrile

INEOS Styrolution Group GmbH

Message:

SAN resin supplied in natural color for use in compounding applications

APPLICATIONS

Compounding

General Information			
Uses	Composite		
Appearance	Natural color		
Processing Method	Composite		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	7.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 23°C)	72.4	MPa	ASTM D638
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength	115	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	43.3	°C	ASTM D1525 ¹
NOTE			

1. 标准 B (120°C/h), 压力 1 (10N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT