

Amilan® CM1017K

Polyamide 6
Toray Resin Company

Message:

Amilan® CM1017K is a Polyamide 6 (Nylon 6) product. It is available in Asia Pacific, Europe, or North America.
Characteristics include:
Flame Rated
Rigid

General Information				
UL YellowCard		E41797-233414		
Features		High Rigidity		
Part Marking Code		>PA6<		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.13	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow				Internal Method
1.00 mm ¹	0.50 to 1.0	--	%	
3.00 mm ²	1.0 to 1.6	--	%	
Water Absorption				ISO 62
23°C, 24 hr	1.8	--	%	
Saturation, 23°C	11	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ISO 2039-2
R-Scale, 80°C	80	--		
R-Scale, 23°C	119	90		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (23°C)	90.0	45.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	25	50	%	ISO 527-2
Flexural Modulus (23°C)	3100	1100	MPa	ISO 178
Flexural Stress (23°C)	120	50.0	MPa	ISO 178
Compressive Stress (23°C)	85.0	--	MPa	ISO 604
Shear Strength (23°C)	75.0	70.0	MPa	ASTM D732
Taber Abrasion Resistance (1000 Cycles)	3.00 to 4.00	--	mg	ISO 9352
Coefficient of Friction - vs. Metal ³	0.150 to 0.200	--		Suzuki Method
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-40°C	2.5	--	kJ/m ²	
23°C	3.5	31	kJ/m ²	

Charpy Unnotched Impact Strength			ISO 179	
-40°C	No Break	--		
23°C	No Break	--		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	194	--	°C	ISO 75-2/B
Melting Temperature	225	--	°C	DSC
CLTE - Flow	8.0E-5	--	cm/cm/°C	ISO 11359-2
Specific Heat	1900	--	J/kg/°C	
Thermal Conductivity	0.25	--	W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+14 to 1.0E+15	1.0E+11 to 1.0E+12	ohms·cm	IEC 60093
Electric Strength	20	--	kV/mm	IEC 60243-1
Dielectric Constant ⁴				IEC 60250
23°C, 50 Hz	4.10	9.00		
23°C, 1 kHz	3.90	8.00		
23°C, 1 MHz	3.40	4.50		
Dissipation Factor ⁵				IEC 60250
23°C, 50 Hz	0.070	0.10		
23°C, 1 kHz	0.060	0.11		
23°C, 1 MHz	0.030	0.13		
Arc Resistance ⁶	120	--	sec	UL 746
Comparative Tracking Index (CTI)	600	--	V	UL 746
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.59 mm)	V-2	--		UL 94
NOTE				
1.	80x80x1mm			
2.	80x80x3mm			
3.	Without Lubrication			
4.	60% RH			
5.	60% RH			
6.	Tungsten Electrode			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

