

Topilene® J440F

Polypropylene Impact Copolymer

Hyosung Corporation

Message:

Characteristics:

Low fisheye

Impact strength

Processability

Applications:

Protective CPP film

| General Information | | | |
|---|---------------|----------|-------------|
| Uses | Film | | |
| Physical | Nominal Value | Unit | Test Method |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 4.5 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Modulus | 1370 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Unnotched Izod Impact | | | ASTM D256 |
| -10°C | 25 | J/m | |
| 23°C | 88 | J/m | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT