

POLYFLAM® RABS 90350 UV5

Acrylonitrile Butadiene Styrene

A. Schulman Europe

Message:

15% mineral filled ABS grade without PBDE

General Information			
UL YellowCard	E86615-463373		
Filler / Reinforcement	Mineral filler, 15% filler by weight		
Features	Good UV resistance		
	Workability, good		
	Good strength		
	Flame retardancy		
UL File Number	E86615		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	20.0	cm ³ /10min	ISO 1133
Water Absorption (23°C, 24 hr)	0.80	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	37.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	2.5	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	4.5	kJ/m ²	ISO 179/1eA
23°C	14	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	40	kJ/m ²	ISO 179/1eU
23°C	75	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	92.0	°C	ISO 75-2/Bf
1.8 MPa, not annealed	77.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	102	°C	ISO 306/A50
--	93.0	°C	ISO 306/B50
Ball Pressure Test (85°C)	Pass		IEC 60695-10-2

RTI Elec			UL 746
1.50 mm	60.0	°C	UL 746
3.00 mm	60.0	°C	UL 746
RTI Imp			UL 746
1.50 mm	60.0	°C	UL 746
3.00 mm	60.0	°C	UL 746
RTI			UL 746
1.50 mm	60.0	°C	UL 746
3.00 mm	60.0	°C	UL 746

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·cm	IEC 60093
Comparative Tracking Index	600	V	IEC 60112

Flammability	Nominal Value	Unit	Test Method
Burning Rate			ISO 3795
1.50mm, automatic fire extinguishing	0.0	mm/min	ISO 3795
3.00mm, automatic fire extinguishing	0.0	mm/min	ISO 3795

Flame Rating			UL 94, IEC 60695-11-10, -20
--------------	--	--	-----------------------------

1.50 mm	V-0		UL 94, IEC 60695-11-10, -20
---------	-----	--	-----------------------------

3.00 mm	V-0		UL 94, IEC 60695-11-10, -20
---------	-----	--	-----------------------------

Glow Wire Flammability Index			IEC 60695-2-12
1.50 mm	960	°C	IEC 60695-2-12
3.00 mm	960	°C	IEC 60695-2-12

Glow Wire Ignition Temperature			IEC 60695-2-13
1.50 mm	675	°C	IEC 60695-2-13
3.00 mm	700	°C	IEC 60695-2-13

Oxygen Index	27	%	ISO 4589-2
--------------	----	---	------------

Additional Information

1.)
Not for use in food contact applications2.)
Not for use in medical or pharmaceutical applications

Injection	Nominal Value	Unit
Drying Temperature	70.0 - 80.0	°C
Drying Time	2.0 - 4.0	hr
Rear Temperature	220	°C
Middle Temperature	230	°C
Front Temperature	240	°C
Nozzle Temperature	240	°C
Processing (Melt) Temp	220 - 240	°C
Mold Temperature	40.0 - 60.0	°C
Injection Pressure	80.0 - 120	MPa

Injection Rate	Slow-Moderate	
Holding Pressure	40.0 - 90.0	MPa
Back Pressure	5.00 - 10.0	MPa
Cushion	< 5.00	mm
Screw Speed		mm/sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

