GELAST GT4HF

Styrene Ethylene Butylene Styrene Block Copolymer Guang Sung Plastics (GSPL)

Message:

GELAST GT4HF is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) product. It can be processed by injection molding and is available in Asia Pacific. Applications of GELAST GT4HF include sporting goods, automotive, consumer goods, handles and household applications. Primary characteristic: rohs compliant.

| General Information | | | |
|-------------------------------------|--------------------------|-------|-------------|
| Features | Good Colorability | | |
| Uses | Automotive Interior Trim | | |
| | Handles | | |
| | Household Goods | | |
| | Sporting Goods | | |
| | Toys | | |
| | Water Sports Equipment | | |
| | | | |
| RoHS Compliance | RoHS Compliant | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.09 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 5 sec) | 43 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus - 100% Secant | 0.873 | MPa | ASTM D638 |
| Tensile Strength | 9.97 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 1100 | % | ASTM D638 |
| Additional Information | Nominal Value | Unit | Test Method |
| Tension Strength | 19.1 | kN/m | ASTM D624 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 220 to 240 | °C | |
| Screw L/D Ratio | 15.0:1.0 | | |
| Screw Compression Ratio | 2.0:1.0 | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

