

Grivory® GVS-5H black 9915

Polyamide 66 + PA 6I/X

EMS-GRIVORY

Message:

Grivory® GVS-5H black 9915 is a Polyamide 66 + PA 6I/X (Nylon 66+Nylon 6I/X) material filled with 50% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion or injection molding.

Important attributes of Grivory® GVS-5H black 9915 are:

Flame Rated

RoHS Compliant

Good Aesthetics

Heat Stabilizer

Typical applications include:

Automotive

Appliances

Consumer Goods

Electrical/Electronic Applications

Engineering/Industrial Parts

General Information	
UL YellowCard	E53898-304749
Filler / Reinforcement	Glass Fiber,50% Filler by Weight
Additive	Heat Stabilizer
Features	Aromatic
	Good Surface Finish
	Heat Stabilized
Uses	Appliance Components
	Automotive Applications
	Automotive Exterior Parts
	Automotive Interior Parts
	Consumer Applications
	Electrical/Electronic Applications
	Engineering Parts
	Household Goods
	Hydraulic Applications
	Industrial Applications
	Pneumatic Applications
	Power/Other Tools
	Sporting Goods
RoHS Compliance	RoHS Compliant
Appearance	Black
Forms	Granules
Processing Method	Extrusion

Injection Molding

Physical	Dry	Conditioned	Unit	Test Method
Density	1.58	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.50	--	%	
Flow	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	4.0	--	%	
Equilibrium, 23°C, 50% RH	1.4	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	280	255	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	17000	16000	MPa	ISO 527-2
Tensile Stress (Break)	250	220	MPa	ISO 527-2
Tensile Strain (Break)	2.5	2.5	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	15	15	kJ/m ²	
23°C	15	15	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	75	60	kJ/m ²	
23°C	90	80	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	240	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	185	--	°C	ISO 75-2/C
Continuous Use Temperature				Internal Method
-- ¹	100 to 120	--	°C	
-- ²	220	--	°C	
Melting Temperature ³	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.5E-5	--	cm/cm/°C	
Transverse	7.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	1.0E+14	ohms · cm	IEC 60093
Electric Strength	33	33	kV/mm	IEC 60243-1

Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA66 + PA6I/X, MH, 14-190, GF50			ISO 1874
NOTE				
1.	Long Term			
2.	Short Term			
3.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

