Solanyl® BP blend 30F

Biodegradable Polymers

Rodenburg Biopolymers B.V.

Message:

Solanyl[®] BP blend 30F is a Biodegradable Polymers (Biodeg Polymers) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding. Primary attribute of Solanyl[®] BP blend 30F: Eco-Friendly/Green.

General Information			
Features	Biodegradable		
Appearance	White		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	
Density	1.26 to 1.30	g/cm³	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	1100 to 1200	MPa	ISO 527-2
Tensile Stress (Yield, Injection Molded)	13.0 to 15.0	MPa	ISO 527-2
Tensile Strain (Break, Injection Molded)	2.5 to 3.0	%	ISO 527-2
Flexural Modulus (Injection Molded)	1200 to 1600	MPa	ISO 178
Flexural Stress (Injection Molded)	32.0 to 40.0	MPa	ISO 178
Flexural Strain at Break - Injection Molded	10 to 14	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (Injection Molded)	8.0 to 12	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	
Heat Deflection Temperature (0.45 MPa, Unannealed)	54.0 to 56.0	°C	
Glass Transition Temperature	55.0 to 56.0	°C	
Melting Temperature (DSC)	140 to 145	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

