

Anjatech® 200C-DT2

Polyamide 6
Almaak International GmbH

Message:

Anjatech® 200C-DT2 is a Polyamide 6 (Nylon 6) material. It is available in Europe.
Important attributes of Anjatech® 200C-DT2 are:
Flame Rated
Impact Modified

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.11	g/cm³	ISO 1183
Water Absorption			ISO 62
23°C, 24 hr	9.5	%	
Equilibrium, 23°C, 50% RH	3.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2/1
Tensile Stress (Yield)	75.0	MPa	ISO 527-2/50
Tensile Strain (Break)	4.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	190	°C	ISO 75-2/B
1.8 MPa, Unannealed	55.0	°C	ISO 75-2/A
Vicat Softening Temperature	190	°C	ISO 306/B50
Melting Temperature	220	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0 to 10	hr	
Suggested Max Moisture	0.10	%	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	80.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

