

NYCOA Polyamide 5015 HS

Polyamide 66

Nycoa (Nylon Corporation of America)

Message:

NYCOA 5015 HS is a 15% glass fiber reinforced, heat stabilized Nylon 66 resin used for injection molding. The heat stabilizer system is specially formulated for optimum thermal stability.

NYCOA 5015 HS is available in UV stable, custom colors, and impact modified grades. It also has excellent chemical resistance to greases, oils, and other hydrocarbons.

NYCOA 5015 HS is suitable for injection molding and can be found in applications in the hardware, and automotive industries.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Additive	heat stabilizer		
Features	Good chemical resistance		
	Hydrocarbon resistance		
	Oil resistance		
	Grease resistance		
	Thermal Stability		
	Thermal stability, good		
Uses	Application in Automobile Field		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.60	%	ASTM D955
Transverse flow	0.80	%	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	120	MPa	ASTM D638
Tensile Elongation ² (Break)	4.0	%	ASTM D638
Flexural Modulus ³	6000	MPa	ASTM D790
Flexural Strength ⁴	174	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, not annealed	249	°C	ASTM D648
1.8 MPa, not annealed	232	°C	ASTM D648
Melting Temperature	260	°C	DSC

Additional Information

The value listed as Melting Point DSC, was tested in accordance with ASTM D789.

Injection	Nominal Value	Unit
Drying Temperature	71.1 - 82.2	°C
Drying Time	4.0 - 6.0	hr
Rear Temperature	266 - 282	°C
Middle Temperature	277 - 293	°C
Front Temperature	288 - 304	°C
Nozzle Temperature	282 - 302	°C
Processing (Melt) Temp	288 - 304	°C
Mold Temperature	76.7 - 87.8	°C
Injection Rate	Fast	
Back Pressure	0.138 - 0.345	MPa
Cushion	1.59 - 6.35	mm
Screw L/D Ratio	16.0:1.0	
Screw Compression Ratio	3.0:1.0	

NOTE

1.	51 mm/min
2.	51 mm/min
3.	51 mm/min
4.	51 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT